

SUBMITTAL SHEET (effective 06/05/07)

**AHC Continuous Rolls**

Physical Properties

Polymer			PVC/NBR
Color			Gray
Classifications			
ASTM D 1056-68			SBE42
ASTM D 1056-00			2B2
Suffix Requirements			
B3, C1, M			
1. 25% Compression Resistance (psi)	ASTM D 1056	7.0 – 9.0	
2. 50% Compression Set (%)	ASTM D 1056	30 max.	
3. Density (lb/ft <sup>3</sup> )	ASTM D 1056	6.5 – 8.5	
4. Water Absorption	ASTM D 1667	0.1 max.	
5. Tensile (psi)	ASTM D 412	90 min.	
6. Elongation (%)	ASTM D 412	100 min.	
7. Flammability (1)			
FMVSS302	0 Burn Rate	Pass	
UL 94	HF-1 @ 1/8"	Pass	
UL 94	V-0 @ 1/2"	Pass	
FAR 25.853 a(2003)	@ 1/4"	Pass	
8. Temperature Use (2)			
ASTM D 1056		Cold Crack	10
		High (3)	200
Standard Roll Widths (in)			56"
Maximum Gauge (in)			1-1/4"

- (1) Flammability – This data refers to typical performance in the specific test indicated. This data should not be construed to imply the behavior of material in other fire conditions. UL 94-test is valid for specific rating and thickness only. See UL 94 listing for details. UL File Number E55475.  
 (2) This recommendation is based on polymer type only. For specific application requirements please contact technical service department.  
 (3) This temperature is the maximum allowable for intermittent exposure only. For continuous use temperature please contact technical service department.

PVC – Polyvinyl Chloride  
 NBR – Acrylonitrile Butadiene Rubber  
 Minimum gauge for skin two sided products is 3/4"  
 Other gauges and widths may be available. Please contact Customer Service.  
 Note: SAEJ 18 is equivalent to ASTM D 1056

For updates to this document please refer to our website.

Armacell provides this information as a technical service. To the extent the information is derived from sources other than Armacell, Armacell is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of Armacell's own technical analysis and testing is accurate to the extent of our knowledge and ability, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. Since Armacell cannot control the end use of this product, Armacell does not guarantee that the user will obtain the same results as published in this document. The data and information is provided as a technical service, and the data and information are subject to change without notice.

Armacell LLC • 1004 Keisler Road • Conover NC 26813  
 email: info.us@armacell.com • www.armacell.com

Conover, NC • 800-992-9116 • fax: 828-465-3199  
 Mebane, NC • 800-973-0490 or 919-304-3846 ext 3972 • fax: 919-304-3847

© 2007 Armacell LLC

AHC	01	06	07	NA	NA
-----	----	----	----	----	----

ALL ARMACELL FACILITIES IN NORTH AMERICA ARE  
 ISO 9001:2000 OR ISO/TS 16949:2002 CERTIFIED

ArmaSport® is a registered trademark of Armacell