

DATA SHEET (effective 7/24/12)

AMC-Med Continuous Rolls

Physical Properties

Polymer				PVC/NBR
Color				Natural
Classifications				
ASTM D 1056-07				2C1/2C2
1. 25% Compression Resistance	psi	ASTM D 1056		4.5 - 6.5
	kPa			31 - 45
2. 50% Compression Set (%)		ASTM D 1056		25 max.
3. Density	lb/ft ³	ASTM D 1056		3.5 - 5.5
	kg/m ³			56 - 88
4. Water Absorption (%)		ASTM D 1056		10 max.
5. Tensile	psi	ASTM D 412 (Die A)		75 min.
	kPa			525 min.
6. Elongation (%)		ASTM D 412 (Die A)		100 min.
7. Flammability (1)				Pass
	FMVSS302	0 Burn Rate		
8. Temperature Use (2)		ASTM D 1056	Cold Crack	0°F (-17°C)
			High Intermittent (3)	200°F (93.3°C)
Standard Roll Widths (in)				64"
Maximum Gauge (in)				1.0" or 1.25"

- (1) Flammability – This data refers to typical performance in the specific test indicated. This data should not be construed to imply the behavior of material in other fire conditions.
 (2) This recommendation is based on polymer type only. For specific application requirements please contact technical service department.
 (3) This temperature is the maximum allowable for intermittent exposure only. For continuous use temperature please contact technical service department.

PVC – Polyvinyl Chloride
 NBR – Acrylonitrile Butadiene Rubber
 Other gauges and widths may be available. Please contact Customer Service.
 Note: SAEJ 18 is equivalent to ASTM D 1056

For updates to this document please refer to our website.

Armacell provides this information as a technical service. To the extent the information is derived from sources other than Armacell, Armacell is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of Armacell's own technical analysis and testing is accurate to the extent of our knowledge and ability, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. Since Armacell cannot control the end use of this product, Armacell does not guarantee that the user will obtain the same results as published in this document. The data and information is provided as a technical service, and the data and information are subject to change without notice.

Armacell LLC • 1004 Keisler Road • Conover NC 26813
 email: info.us@armacell.com • www.armacell.com

Conover, NC • 800-992-9116 or 919-304-3846 ext 3110 • fax: 828-465-3199
 Mebane, NC • 800-973-0490 or 919-304-3846 ext 3972 • fax: 919-304-3847

© 2012 Armacell LLC

AMC-Med	01	07	12	NA	NA
---------	----	----	----	----	----

ALL ARMACELL FACILITIES IN NORTH AMERICA ARE
 ISO 9001:2000 OR ISO/TS 16949:2002 CERTIFIED

ArmaSport® is a registered trademark of Armacell