

Xcellite_™ XB41 Typical Data Sheet

Engineered Foam Description Soft cellular rubber

Polymer PVC/NBR (Polyvinyl Chloride/Acrylonitrile Butadiene)

Standard Color Black (Please call for optional colors)

ASTM D1056 Classification 2B1/2C1 (optional suffixes can be added)

| Physical Property | Target | Units | Test Method |
|--------------------------------------|---------------------------|---------------------|---------------|
| Density | 48 - 80 | kg/m ³ | ASTM D1056 |
| | 3 - 5 | lbs/ft ³ | |
| Compression Deflection,25% | 15 - 35 | kPa | ASTM D1056-07 |
| | 2 - 5 | psi | |
| Compression Set, 50% RT | 25 | % | ASTM D1056 |
| Tensile | 275 | kPa | ASTM D1056 |
| | 40 | psi | |
| Elongation | 125 | % | ASTM D1056 |
| Water Absorption | 10 max. | % | ASTM D1056 |
| Flammability, burn rate | 0 - SE | mm/min. | FMVSS 302 |
| | 0 - SE | in./min. | |
| Temperature Use: Hot ¹ | 93 / 200 | °C / °F | |
| : Cold | -40 / -40 | °C / °F | ASTM D1056 |
| Gauge ^{2, 3} skin two sides | 19 - 44 (+5,-0) | mm | ASTM D1056 |
| | 0.750 - 1.750 (+0.200,-0) | in. | |

NOTE:

- 1 For intermittent exposure only
- 2 Please contact customer service 574.284.1000 for additional sizes including widths, skin one side and no skin surfaces.
- 3 RMA Class 3 surfaces

For reference:

MS-AY516 Type I - Chrysler Engineering Approved Source

GMW15473 Class 2 Type 4 with deviations

GM6086M Type II

SAE J18 2B1

For details or information on additional standards please contact customer service.

The technical service information presented on this Typical Data Sheet has been derived from data using standardized test methods/practices. Fostek Corp. does not control the end use/modification of its products and therefore does not represent or warrant its products to be suitable for any specific end use. Fostek recommends that its material be tested for fitness of use and safety in the manner in which it may be utilized.





