



Developer & Manufacturer of Engineered Foams

Xcellite™ XUBU Typical Data Sheet

Engineered Foam Description Medium cellular rubber
 Polymer PVC/NBR (Polyvinyl Chloride/Acrylonitrile Butadiene)
 Standard Color Green (Please call for optional colors)

ASTM D1056 Classification 2B1/2B2 (optional suffixes can be added)

Physical Property	Target	Units	Test Method
Density	96 - 136	kg/m ³	ASTM D1056
	6.0 - 8.5	lbs/ft ³	
Compression Deflection,25%	25 - 55	kPa	ASTM D1056-07
	4.0 - 8.0	psi	
Compression Set, 50% RT	25	%	ASTM D1056
Tensile	515	kPa	ASTM D1056
	75	psi	
Elongation	100	%	ASTM D1056
Water Absorption	10 max.	%	ASTM D1056
Flammability, burn rate	0 - SE	mm/min.	FMVSS 302
	0 - SE	in./min.	
Temperature Use: Hot ¹	93 / 200	°C / °F	
: Cold	-30 / -22	°C / °F	ASTM D1056
Gauge ^{2,3} skin two sides	19 - 38 (+5,-0)	mm	ASTM D1056
	0.750 - 1.500 (+0.200,-0)	in.	

NOTE:

- 1 - For intermittent exposure only
- 2 - **Please contact customer service 574.284.1000 for additional sizes including widths, skin one side and no skin surfaces.**
- 3 - RMA Class 3 surfaces

For reference:

SAE J18 2B2/2C2

For details or information on additional standards please contact customer service.

The technical service information presented on this Typical Data Sheet has been derived from data using standardized test methods/practices. Fostek Corp. does not control the end use/modification of its products and therefore does not represent or warrant its products to be suitable for any specific end use. Fostek recommends that its material be tested for fitness of use and safety in the manner in which it may be utilized.



☎: 618-282-7700

✉: sales@seconrubber.com

🌐: www.seconrubber.com