



PHYSICAL PROPERTIES CHART

DURAFOAM™ F86

Effective Date: January, 1, 2011

TYPICAL PHYSICAL PROPERTIES	Test Method	DURAFOAM™ F86
Polymer		PVC/NBR
Color		Black or Tan
Specifications: ASTM-D-1056-07		SCE41 2C1 B3, C1, M
Compression Deflection, 25% PSI Compression	ASTM-D-1056	2 to 5 psi
50% Compression Set	ASTM-D-1056	28% max.
Density (lb/ft3)	ASTM-D-1056	4.5 to 6.5
Tensile (psi)	ASTM-D-412	75 min.
Elongation (%)	ASTM-D-412	180 min.
Flammability, FMVSS302 (1)	0 Burn Rate	Pass

Note: (1) Flammability – Typical performance under specific test requirements. Results should not be interpreted to imply the same results under other fire conditions.

This data and information is provided as a technical service and is subject to change without notice. Some of the above information may be provided from outside sources and MRPC relies on those sources to provide accurate information. Test results provided based on our own lab testing is believed to be accurate and is provided to the best of our ability based on our knowledge of the test methods and specifications listed. However, please keep in mind that some materials have unique physicals that are not part of the recognized industry specifications and standards. Therefore customer sample evaluation and approval of any material is suggested. MRPC will provide free of charge samples of its materials to assist customers in their evaluation to determine the safety, fitness and suitability of the product for the application and use by the user and by any third party which may use the product. MRPC cannot control the final use of the product and, therefore, does not guarantee the performance or the exact duplication of the results published in this document. For technical evaluation and support, please contact John M. Bonforte, Sr, Ext. 12 or email: johnsr@monmouthrubber.com

DURAFOAM™ F86 IS HCFC FREE

AND 100% RECYCLABLE



☎: 618-282-7700

✉: sales@seconrubber.com

➦: www.seconrubber.com