

September 2012



TYPICAL PHYSICAL PROPERTIES
DURAFOAM™ IVN41

PHYSICALS	TEST	DURAFOAM™ IVN 41
POLYMER		NEO/PVC/NBR
COLOR		BLACK
SPECIFICATIONS: ASTM-D-1056-68 ASTM-D-1056-07 Suffix Requirements		SBE41 2B1 C1, F1, M
COMPRESSION RESISTANCE, 25% (psi)	ASTM-D-1056	2.0 to 5.0 psi
COMPRESSION SET, (%)	ASTM-D-1056	40 max.
DENSITY (lb/ft3)	ASTM-D-1056	3.0 to 5.0
WATER ABSORPTION (lb/ft2)	ASTM-D-1667	0.1 max.
TENSILE	ASTM-D-412	40 min.
ELONGATION	ASTM-D-412	100 min.
FLAMMABILITY: FMVSS302 UL94 FAR 25.853 (a) Appendix F, Part 1 (in)	0 Burn Rate HFB @ 1/8"	Pass Pass 1/4
TEMPERATURE USE	ASTM-D-1056	Cold Crack -40 High +200
K FACTOR (BTU)		0.27 Constant

DISCLAIMER: To the extent that the above product information is derived from sources other than Monmouth Rubber, Monmouth Rubber is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of Monmouth Rubber's own technical analysis and testing is accurate to the extent of our knowledge and ability, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. Since Monmouth Rubber cannot control the end use of this product, Monmouth Rubber does not guarantee that the user will obtain the same results as published in this document. The data and information is provided as a technical service, and the data and information is subject to change without notice. When considering the above product as a competitive equivalent material, please keep in mind that some materials have unique physicals that are not part of the recognized industry specifications and standards. Therefore, customer sample evaluation and approval of any substitution is suggested. Monmouth Rubber will supply free of charge evaluation & testing of its materials to assist customers in their evaluation. For technical evaluation and support, please contact John M. Bonforte, Sr., Ext. 12, or email: johnsr@monmouthrubber.com.

“0” EMISSIONS – GUARANTEED TO BE 100% RECYCLABLE



ISO CERTIFIED 9001:2008
CERTIFICATE #US08/5033



☎: 618-282-7700
✉: sales@seconrubber.com
➡: www.seconrubber.com