

**TECHNICAL DATA SHEET** (effective 7/19/19)

**CLJN 300 Continuous Rolls/Sheets**

Polymer: Polyethylene

Physical Property	Units	Test Method	Typical Properties
Density	lb./ft <sup>3</sup>	ASTM D 3575 Suffix W	3.0
	kg/m <sup>3</sup>	ASTM D 3575 Suffix W	48.0
Tensile Strength	psi	ASTM D 3575 Suffix T	75.0
	kPa	ASTM D 3575 Suffix T	517.0
Elongation	%	ASTM D 3575 Suffix T	158
Tear Resistance	lb./in.	ASTM D 3575 Suffix G	18.9
	kN/m	ASTM D 3575 Suffix G	3.3
Compressive Strength			
25% Deflection	psi	ASTM D 3575 Suffix D	8.3
40% Deflection	psi	ASTM D 3575 Suffix D	12.9
Compression Set	%	ASTM D 3575 Suffix B	TBD
Thermal Stability, % change (24 hours @ 158°F)	%	ASTM D 3575 Suffix S	TBD
Water Absorption (skived)	lb. /sq. ft.	ASTM D 3575 Suffix L	TBD
Flammability	Burn rate	FMVSS 302 (0.062" thickness)	TBD

Properties are averages of machine and cross direction.  
 Values shown are typical.

All data and technical information are based on results achieved under typical application conditions. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. By ordering/receiving product you accept the Armacell General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these.

© 2019 Armacell OleTex<sup>®</sup> is a registered trademark of the Armacell Group.

**For more information:**  
[www.armacell.us](http://www.armacell.us)  
[info.cf.us@armacell.com](mailto:info.cf.us@armacell.com)  
 800-973-0490