## **UPPER-TEMPERATURE INSULATION**

# UT SolaFlex

## Tube and Roll Insulation

Flexible, closed-cell elastomeric insulation for protection against condensation, mold, energy loss and ultraviolet radiation in upper-temperature applications. UT Solaflex is PVC free.

- // 300°F upper temperature limit ideal for solar applications, hot gas piping, low pressure steam lines and VRV/VRF applications
- // Effectively retards degradation due to ultraviolet radiation
- // EPDM-based, closed-cell structure provides excellent condensation control and prevents energy loss
- // Meets 25/50 flame and smoke index ASTM E84

www.armacell.us













#### TECHNICAL DATA - UT SOLAFLEX TUBE AND ROLL INSULATION

#### Description

Black, EPDM-based, flexible, closed-cell elastomeric thermal insulation in tubular and roll form

#### Applications

Pipe insulation for: Variable Refrigerant Flow (VRF), Variable Refrigerant Volume (VRV), solar hot water, HVAC hot gas and low pressure steam, dual temperature lines

#### Approvals, Certifications, Compliances

- GREENGUARD Gold Certified
- Manufactured without CFCs, HFCs, HCFCs, PBDEs, or Formaldehyde
- ASTM C 534 Type I (Tubular) Grade 2, Type II (Sheet) Grade 2

- Rated for use in return air plenums
- Meets Living Building Challenge requirements
- All Armacell facilities in North America are ISO 9001 certified

#### **Typical Properties**

Specifications	Values	Test Method		
Thermal Conductivity: Btu • in/h • ft2 • °F (W/mK)				
75°F Mean Temperature (24°C) 100°F Mean Temperature (38°C)	0.28 (.040) 0.288 (0.0415)	ASTM C 177 or C 518		
<b>Water Vapor Permeability:</b> Perm-in. [Kg/(s • m • Pa)]	0.08 (1.16 x 10 <sup>-13</sup> ) ASTM E 96, Procedure A			
Flame Spread and Smoke Developed Index:	25/50 rated	ASTM E 84, UL 723, and NFPA 255		
Water Absorption, % by Volume:	0.2 %	ASTM C1763 Procedure B		
Mold Growth: Fungi Resistance: Bacterial Resistance:	Passed	UL181 ASTM G21/C1338		
Upper Use Limit: ①	300°F (150°C)	ASTM C534		
Lower Use Limit: ②	-297°F (-183°C) <sup>③</sup>	ASTM C534		
Ozone Resistance:	Excellent	ASTM D 1149		
UltraViolet (UV) Resistance	Excellent	ASTM G90		

#### **Sizes**

Tubes		Rolls	
Wall Thickness (nominal)	1/2", 3/4" and 1" (13, 19 and 25 mm)	Width	48" (1.22m)
Inside Diameter, Tubular	1/4" through 2-1/2" IPS ( 6 mm through 73 mm)	Thickness x Length	1/2" x 70' (13 mm x 21.3 m)
Length of Sections, Tubular	6' (1.83 m)	-	3/4" x 50' (19 mm x 15.2 m) 1" x 35' (25 mm x 10.7 m)
Outdoor Use	Painting with WB Finish or other protective jacketing is required to prevent damage to the insulation in exterior applications and to		

© Suitable for systems with occasional or intermittent temperatures to 350° F (175° C), with a recommended exposure limit of one 30 minute period at 350° F (175° C) over 24 hours of operation.

comply with the insulation protection sections of the International Energy Conservation Code (IECC) and ASHRAE 90.1.

All data and technical information are based on results achieved under typical application conditions. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. By ordering/receiving product you accept the **Armacell General Terms and Conditions** of Sale applicable in the region. Please request a copy if you have not received these.

© Armacell, 2019. UT SolaFlex | SolaFlex | TDS | 122019 | NA | EN-A | 028

### ABOUT ARMACELL

As the inventors of flexible foam for equipment insulation and a leading provider of engineered foams, Armacell develops innovative and safe thermal, acoustic and mechanical solutions that create sustainable value for its customers. Armacell's products significantly contribute to global energy efficiency making a difference around the world every day. With 3,100 employees and 24 production plants in 16 countries, the company operates two main businesses, Advanced Insulation and Engineered Foams. Armacell focuses on insulation materials for technical equipment, high-performance foams for high-tech and lightweight applications and next generation aerogel blanket technology.



② At temperatures below -20° F (-29° C), elastomeric insulation starts to become less flexible. However, this characteristic does not affect thermal efficiency or water vapor permeability of UT Solaflex insulation.