

DATA SHEET

EPDM

(Ethylene Propylene Diene Terpolymer)

4215-EC

Color:		Black
Specifications:	ASTM D-1056-00	2A2
25% Compression Deflection (PSI)		5 - 9
Shore 00 Durometer (Approximate)		40 - 60
Density (Approximate p.c.f.)		9 - 14
Water Absorption By Weight		5%
Temperature Range		-90 to 275 F
Weather Resistance:	UV Ozone	Excellent Excellent
Tensile Strength (Typical)		65 PSI
Elongation (Typical)		180%
Flammability:	FM VSS No. 302	Pass

Temperature range listed is continuous. Moderately higher or lower temperatures are attainable on an intermittent basis.

American National Rubber disclaims responsibility for results of use of this information, which is furnished without charge, or of any product mentioned herein. It is the user's responsibility to make and be guided by his own testing before making a final decision on the type of material to be used in any application.

10/2014



☎: 618-282-7700

✉: sales@seconrubber.com

🌐: www.seconrubber.com