

DATA SHEET

| EPDM (Ethylene Propylene Diene Terpolymer) | | 4315-E |
|---|---|---|
| Color: | | Black |
| Specifications: | ASTM D-1056-00 ASTM D-1056-67 ₍₁₎ SAE J18-02 GM 6086M ₍₃₎ GMN11106(3) TSM1501G | 2A3 RE43 2A3 IIIA IIIA 2A3 |
| 25% Compression Deflection (PSI) | | 9 - 13 |
| Shore 00 Durometer (Approximate) | | 45 - 65 |
| Density (Approximate p.c.f. |) | 12 - 20 |
| Water Absorption By Weight | | 5% |
| Temperature Range | | -90 to 275 F |
| Weather Resistance: | UV Ozone | Excellent Excellent |
| Accelerated Linear Shrinkage (Typical) | | 5% |
| Tensile Strength (Typical) | | 70 PSI |
| Elongation (Typical) | | 200% |
| Flammability: | FM VSS No. 302 | Pass |

(1)Obsolete specification listed for reference only. ANR certifies to most recent revision of ASTM D-1056 and SAE J18.

(3) Certain sections of this specification will not apply to all products. Contact Customer Service for details.

American National Rubber disclaims responsibility for results of use of this information, which is furnished without charge, or of any product mentioned herein. It is the user's responsibility to make and be guided by his own testing before making a final decision on the type of material to be used in any application.



