



**MANUFACTURER OF
CLOSED CELL SPONGE RUBBER
& PLASTIC FOAM**



MARCH 2016

**DURAFOAM™ CLOSED CELL
LOW DENSITY 100% EPDM, THERMOFORMABLE**

PHYSICAL PROPERTIES	DURAFOAM™ P1921LDTF, P1924LDTF
Polymer	100% EPDM
Color – Black	P1921LDTF
Color – Tan	P1924LDTF
ASTM-D 1056-67 ASTM-D 1056-14 Suffix Requirements	RE-42 2A2 C1, F2, M, P
25% Compression Deflection (PSI)	5-9 PSI
Density (lb/ft ³) approx.	5
Water Absorption	Under 5%
Tensile (PSI)	50 min
Elongation % Min	300%
Flammability – FMVSS302	PASS
Ozone Resistance: Ozone 20% Stress, 72 HRS @ 100 PPHM, ASTM-D-1171-94; 1149-91; GM6086M; GM4486P; CHRYSLER MSAY 527	EXCELLENT 0 CRACKS PASS
Low Temp – Cold Bend 5 HRS Per ASTM-D 1056-14	-90°F
Split Tear	13.8lbs/in.

GUARANTEED 100% RECYCLABLE

DISCLAIMER: To the extent that the above product information is derived from sources other than Monmouth Rubber, Monmouth Rubber is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of Monmouth Rubber's own technical analysis and testing is accurate to the extent of our knowledge and ability, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. Since Monmouth Rubber cannot control the end use of this product, Monmouth Rubber does not guarantee that the user will obtain the same results as published in this document. The data and information is provided as a technical service, and the data and information is subject to change without notice. When considering the above product as a competitive equivalent material, please keep in mind that some materials have unique physicals that are not part of the recognized industry specifications and standards. Therefore, customer sample evaluation and approval of any substitution is suggested. Monmouth Rubber will supply free of charge evaluation & testing of its materials to assist customers in their evaluation. For technical evaluation and support, please contact John M. Bonforte, Sr., Ext. 12, or email: johnsr@monmouthrubber.com.



**ISO CERTIFIED 9001:2008
CERTIFICATE #US08/5033**



☎: 618-282-7700
✉: sales@seconrubber.com
🌐: www.seconrubber.com